



**LORK  
INDUSTRIAS**



[www.lorkindustrias.com](http://www.lorkindustrias.com)

**LORK INDUSTRIAS, S.L.**  
CARACAS, 11  
08030—BARCELONA  
SPAIN  
Telefono: 0034 93 346 82 12  
Fax: 0034 93 311 30 60  
Email: [lork@lorkindustrias.com](mailto:lork@lorkindustrias.com)

## DATA SHEET

# ASLAGLASS

### Composition

Asbestos free millboard based on mineral fibres

### Characteristics

|  |              |                    |             |
|--|--------------|--------------------|-------------|
| Density  |              | g/cm <sup>3</sup>  | 0,95        |
| Classification Temperature   |              | C°                 | 750         |
| Colour   |              |                    | Light brown |
| Tensile Strength   | longitudinal | Kg/cm <sup>2</sup> | 40          |
|  | transversal  | Kg/cm <sup>2</sup> | 30          |
| Shrinkage at 1000°C 24 h   |              | %                  | <1          |
| Compressibility according ASTM F36 (Method 70 kg/cm <sup>2</sup> ) |              | %                  | 10          |
| Recovery   |              | %                  | 40          |
| Heat treatment loss at 800°C                                       |              | %                  | 12          |